

# Crown Crack Sealer™

## Product Description Sheet No. 120



**RAPID CURING HIGH STRENGTH EPOXY, SMOOTH PASTE ADHESIVE BONDS INJECTION PORTS TO CRACKED CONCRETE AND WOOD SEALS CRACK OPENING AND FILLS SURFACE ROUTED NON-MOVING CRACKS**

### DESCRIPTION

**Crown Crack Sealer, Product No 120** is a 100% solids, non-shrink, non-sag, moisture insensitive, two-component modified high-modulus smooth epoxy paste adhesive formulated to adhere and cure on damp or dry surfaces.

### WHERE TO USE

- Used to seal the surface opening of cracks and to secure injection ports on concrete and wood prior to pressure injection grouting.
- Used on non-structural and structural grouting projects.
- Use to seal routed crack surfaces on non-moving cracks.

### ADVANTAGES

- Paste consistency ideal for horizontal, vertical and overhead crack sealing.
- Very rapid curing for faster pressure injection grouting.
- Cures and adheres on dry or damp surfaces.
- Injection may proceed after approximately 30 minutes.
- Convenient 2 to 1 volume mix ratio.
- Excellent adhesion to wood, masonry, concrete, steel and most building substrates.
- Applicable / Curable down to 20°F (-6°C)

### TYPICAL DATA FOR Crown Crack Sealer

(Material and Curing Conditions at 73°F unless noted, 50% R.H.)

**COLOR** Concrete Gray **WORKING TIME** 3-5 minutes

**CONSISTENCY** Paste **NON-SAG** Neat 1/2 in.

#### TACK-FREE TIME

Substrate Temperature	20°F	40°F	55°F	73°F
	6-7 hrs.	3 hrs	30-60 mins.	30 mins.

#### TENSILE PROPERTIES (ASTM D 638) 5 Days

Tensile Strength	3,400 psi (23.4 MPa)
Elongation at Break	1.1 %

#### FLEXURAL PROPERTIES (ASTM D 790) 5 Days

Flexural Strength	4,600 psi (31.7 MPa)
Tangent Modulus of Elasticity	1.6 X 10 <sup>6</sup>

#### WATER ABSORPTION (ASTM D 570)

24 hours	0.45%
----------	-------

#### DEFLECTION TEMPERATURE (ASTM D 648) 5 DAYS

Fiber Stress Loading = 264 psi	140°F
--------------------------------	-------

**SHELF LIFE** 1.5 years in original unopened containers.  
Cartridges 1 year.

#### PACKAGING and YIELDS

##### Cartridges for Hand Dispensing Tool

10 Two-Component Cartridges/Case Each Cartridge contains 30 in<sup>3</sup>

##### Cartridges for Power Pumping Jake Dispensing Unit

7 Two-Component Cartridges/Case Each Cartridge contains 120 in<sup>3</sup>

##### Bulk Containers

3 Gallon Unit - Each Gallon contains 231 in<sup>3</sup>  
15 Gallon Unit

# How To Use Crown Crack Sealer, Product No. 120

## SURFACE PREPARATION

Concrete, stone, wood and other substrates must be clean and sound. Remove dust, grease, waxes, oils, concrete laitance, curing compounds, coatings and all contaminants by mechanical means such as bush hammering, grinding or abrasive blasting. Apply epoxy before the cleaned substrate becomes contaminated.

## LIMITATIONS

- Minimum substrate & ambient temperature is 20°F (-6°C)
- **DO NOT THIN** - solvents will prevent proper cure.
- **DO NOT PLACE EPOXY IF ICE IS PRESENT.**

## PRECONDITIONING EPOXY

When temperatures drop, it becomes harder to spread the epoxy. To improve the flow-ability and curing time at lower temperatures preheat each epoxy component to 90°F (32°C) before mixing. Caution the working time (potlife) will be reduced by about 50%. Preheat product before mixing and use when temperature is below 65°F (18°C). It does not affect the epoxy when a static mixing tube is used.

## MECHANICAL MIXING

Pre-mix each component. Place one part component "B" into 2 parts component "A" and mix for 1 minute with a low speed paddle attached to a drill (300-600 rpm) until a uniform color develops with out any streaks. Mix only that quantity that can be used within its potlife. Smaller quantity requirement may be mixed with hand tools.

## CARTRIDGE MIXING

Remove nut and plugs on dispersing end of cartridge. Place static mixing tube (nozzle) on end of cartridge unit, slip nut over mixing tube and tighten nut by hand to secure mixing tube in place. Dispense at least one static mixing tube quantity full of epoxy or a sufficient amount until one color without streaks develops to start the correct mixing process. Immediately place the epoxy.

**Option:** The premeasured two components may be pumped directly out of the cartridge unit without a static mixing tube onto a piece of cardboard, mixed with a hand tool and immediately placed. No nozzle is required.

## APPLICATION

- **Surface Seal**
  1. Set injection ports over the cracked surface.
  2. Apply the mixed epoxy sealer "**Crown Crack Sealer**", to the cleaned surfaces to be sealed and around the ports. Spread the product evenly over the crack, on each side of the crack, and down into the upper surface area of the crack for best sealing results.
  3. When the tack-free cure development has occurred the crack may be pressure grouted.

- **Routed Crack Sealing**

On cracks that do not move fill the routed void with mixed epoxy and trowel the surface smooth to the adjacent substrate edges. The surface may be used upon the epoxy developing its tack-free cure.

## CAUTION

**Before Using Read Material Safety Data Sheets.**

**Component "A" - Irritant**  
Contains epoxy resins. Prolonged contact with skin may cause irritation. Avoid contact with eyes.

**Component "B" - Corrosive**  
Contains aliphatic and other amines. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer

## IMPORTANT INFORMATION

Use of safety goggles, chemical-resistant gloves, adequate ventilation. NIOSH/MSHA approved respirator is recommended when ventilation is not adequate.

## FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. For respiratory problems, remove person to fresh air. Contact Physician Immediately. Wash clothing before re-use.

## CLEAN-UP

**Components "A" & "B" -**  
Ventilate area. Control spills. Collect with absorbent material.

## Disposal

Dispose in accordance with current, applicable local, state, and federal regulations.

**KEEP OUT OF REACH OF CHILDREN**

**FOR INDUSTRIAL USE ONLY**

LIMITED WARRANTY - "Crown Polymers, LLC warrants its products to be free of manufacturing defects, to be of good quality, and that they will meet Crown Polymers current published physical properties when applied in accordance with Crown Polymers written directions and tested in accordance with ACI, ASTM and Crown Polymers Standards. Product proved to be defective will be replaced. **There are no other warranties by Crown Polymers, LLC of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product.** Crown Polymers, LLC shall not be liable for damages of any sort, including remote or consequential damages, resulting from any claimed breach of any warranty, whether expressed or implied, from any other cause whatsoever. Crown Polymers will not be responsible for use of this product in a manner to infringe on any patent held by others."

For the Location of Your Nearest Crown Polymers Representative



**CALL NATIONWIDE TOLL-FREE 1-888 / 732-1270**